



2 Flute: High Shear 4 Flute: High Shear



Series 52M, 54M Metric	Hardness	Flutes	Ae x DC	Ap x DC	Vc (m/min)	DC • mm								
						3	6	10	12	20	25			
ALUMINUM ALLOYS 2024, 5052, 5086, 6061, 6063, 7075	≤ 150 Bhn or ≤ 7 HRc	Profile 			415	RPM	43947	21973	13184	10987	6592	5274		
						Fz	0.0166	0.043	0.091	0.110	0.147	0.160		
						Feed (mm/min)	1459	1890	2399	2417	1938	1688		
			Slot 			332	RPM	35222	17611	10567	8806	5283	4227	
						Fz	0.0151	0.041	0.085	0.101	0.133	0.148		
						Feed (mm/min)	1064	1444	1796	1779	1405	1251		
	ALUMINUM DIE CAST ALLOYS (HIGH SILICON) A-390, A-392, B-390	≤ 125 Bhn or ≤ 77 HRb	Profile 			155	RPM	16480	8240	4944	4120	2472	1978	
							Fz	0.0166	0.043	0.091	0.110	0.147	0.160	
							Feed (mm/min)	547	709	900	906	727	633	
				Slot 			125	RPM	13249	6624	3975	3312	1987	1590
							Fz	0.0151	0.041	0.085	0.101	0.133	0.148	
							Feed (mm/min)	400	543	676	669	529	471	
COPPER ALLOYS Aluminum Bronze, Muntz Brass, Naval, Brass, Red Brass		≤ 140 Bhn or ≤ 3 HRc	Profile 			180	RPM	19065	9533	5720	4766	2860	2288	
							Fz	0.0094	0.024	0.053	0.062	0.083	0.093	
							Feed (mm/min)	358	458	606	591	475	426	
				Slot 			145	RPM	15349	7675	4605	3837	2302	1842
							Fz	0.0086	0.024	0.048	0.058	0.077	0.085	
							Feed (mm/min)	264	368	442	445	355	313	
	COPPER ALLOYS Beryllium Copper, C110, Manganese Bronze, Tin Bronze	≤ 200 Bhn or ≤ 23 HRc	Profile 			72	RPM	7594	3797	2278	1898	1139	911	
							Fz	0.0094	0.024	0.053	0.062	0.083	0.093	
							Feed (mm/min)	143	182	241	235	189	169	
				Slot 			58	RPM	6140	3070	1842	1535	921	737
							Fz	0.0086	0.024	0.048	0.058	0.077	0.085	
							Feed (mm/min)	106	147	177	178	142	125	

continued on next page

2 Flute: High Shear 4 Flute: High Shear



Series 52M, 54M Metric	Hardness	Flutes	Ae x DC	Ap x DC	Vc (m/min)	DC • mm								
						3	6	10	12	20	25			
PLASTICS ABS, Polycarbonate, PVC, Polypropylene	Profile	2	≤ 0.3	≤ 1.5	488	RPM	51702	25851	15511	12926	7755	6204		
					Fz	0.0264	0.072	0.149	0.178	0.237	0.250			
		4	≤ 0.3	≤ 1.5	(390-585)	Feed (mm/min)	2730	3723	4622	4601	3676	3102		
					Fz	5460	7445	9244	9203	7352	6204			
		Slot	2	1	≤ 1	390	RPM	41362	20681	12409	10340	6204	4963	
						Fz	0.0240	0.065	0.136	0.163	0.210	0.238		
	4		1	≤ 0.25	(312-468)	Feed (mm/min)	1985	2689	3375	3371	2606	2363		
					Fz	3971	5377	6750	6742	5212	4725			
	PLASTICS Fiberglass, Glass Filled		Profile	2	≤ 0.3	≤ 1.5	219	RPM	23266	11633	6980	5816	3490	2792
							Fz	0.0197	0.053	0.109	0.132	0.173	0.190	
		4		≤ 0.3	≤ 1.5	(176-263)	Feed (mm/min)	917	1233	1522	1536	1208	1061	
						Fz	1833	2466	3043	3071	2415	2122		
Slot		2		1	≤ 1	175	RPM	18580	9290	5574	4645	2787	2230	
						Fz	0.0180	0.048	0.101	0.120	0.160	0.175		
		4	1	≤ 0.25	(140-210)	Feed (mm/min)	669	892	1126	1115	892	780		
					Fz	1338	1784	2252	2230	1784	1561			

Bhn (Brinell) HRC (Rockwell C) HRB (Rockwell B)
 $rpm = (Vc \times 1000) / (DC \times 3.14)$
 $mm/min = Fz \times \text{number of flutes} \times rpm$
 reduce speed and feed for materials harder than listed
 reduce feed and Ae when finish milling (.02 x DC maximum)
 refer to the SGS Tool Wizard® for complete technical information (www.kyocera-sgstool.com)