



# FRACTIONAL & METRIC Z-Carb-MD



Series ZD1CR Fractional	Hardness			Vc (sfm)	Diameter (DC) (inch)								
		Ae x DC	Ap x DC		1/8	1/4	3/8	1/2	5/8	3/4			
TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375 Bhn or ≤ 40 HRc	Profile 	≤ 0.4	≤ 1	405	RPM	12377	6188	4126	3094	2475	2063	
					(324-486)	Fz	0.0005	0.0012	0.0023	0.0030	0.0039	0.0042	
		320	RPM	9779	4890	3260	2445	1956	1630				
	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 475 Bhn or ≤ 50 HRc	Slot 	1	≤ 0.4	(256-384)	Fz	0.0005	0.0012	0.0023	0.0030	0.0039	0.0042
							Feed (ipm)	19.6	23.5	30.0	29.3	30.5	27.4
			TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 655 Bhn or ≤ 60 HRc	Profile 	≤ 0.4	≤ 1	210	RPM	6418	3209	2139	1604
(168-252)	Fz	0.0004						0.0010	0.0019	0.0025	0.0032	0.0035	
170	RPM	5195			2598	1732	1299	1039	866				
TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 655 Bhn or ≤ 60 HRc	Slot 		1	≤ 0.4	(136-204)	Fz	0.0004	0.0010	0.0019	0.0025	0.0032	0.0035
							Feed (ipm)	8.3	10.4	13.2	13.0	13.3	12.1
		TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2		≤ 655 Bhn or ≤ 60 HRc	Profile 	≤ 0.4	≤ 1	90	RPM	2750	1375	917	688
(72-108)	Fz		0.0002					0.0005	0.0010	0.0013	0.0017	0.0018	
70	RPM		2139		1070	713	535	428	357				
TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 655 Bhn or ≤ 60 HRc		Slot 	1	≤ 0.4	(56-84)	Fz	0.0002	0.0005	0.0010	0.0013	0.0017	0.0018
							Feed (ipm)	1.7	2.1	2.9	2.8	2.9	2.6

Bhn (Brinell)    HRc (Rockwell C)  
 $rpm = Vc \times 3.82 / DC$   
 $ipm = Fz \times 4 \times rpm$   
 reduce speed and feed for materials harder than listed  
 reduce feed and Ae when finish milling (.02 x DC maximum)  
 feed rates listed have chip thinning adjustments included where applicable  
 refer to the SGS Tool Wizard® for complete technical information (www.kyocera-sgstoool.com)



Series ZD1MCR Metric	Hardness			Vc (m/min)	Diameter (DC) (mm)									
		Ae x DC	Ap x DC		3	6	8	10	12	16	20			
TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375 Bhn or ≤ 40 HRc	Profile 	≤ 0.4	≤ 1	123	RPM	13087	6544	4908	3926	3272	2454	1963	
					(99-148)	Fz	0.012	0.029	0.049	0.061	0.072	0.083	0.112	
		98	RPM	10340	5170	3878	3102	2585	1939	1551				
	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 475 Bhn or ≤ 50 HRc	Slot 	1	≤ 0.4	(78-117)	Fz	0.012	0.029	0.049	0.061	0.072	0.083	0.112
							Feed (mm/min)	496	596	761	761	744	645	695
			TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 655 Bhn or ≤ 60 HRc	Profile 	≤ 0.4	≤ 1	64	RPM	6786	3393	2545	2036	1696
(51-77)		Fz						0.010	0.024	0.041	0.051	0.060	0.068	0.093
52		RPM			5493	2747	2060	1648	1373	1030	824			
TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2		≤ 655 Bhn or ≤ 60 HRc		Slot 	1	≤ 0.4	(41-62)	Fz	0.010	0.024	0.041	0.051	0.060	0.068
							Feed (mm/min)	211	264	334	334	330	281	308
	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2			≤ 655 Bhn or ≤ 60 HRc	Profile 	≤ 0.4	≤ 1	27	RPM	2908	1454	1091	872	727
(22-33)		Fz	0.005					0.012	0.021	0.027	0.031	0.036	0.048	
21		RPM	2262		1131	848	679	565	424	339				
TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2		≤ 655 Bhn or ≤ 60 HRc	Slot 	1	≤ 0.4	(17-26)	Fz	0.005	0.012	0.021	0.027	0.031	0.036	0.048
							Feed (mm/min)	43	54	72	72	71	62	65

Bhn (Brinell)    HRc (Rockwell C)  
 $rpm = (Vc \times 1000) / (DC \times 3.14)$   
 $ipm = Fz \times 4 \times rpm$   
 reduce speed and feed for materials harder than listed  
 reduce feed and Ae when finish milling (.02 x DC maximum)  
 feed rates listed have chip thinning adjustments included where applicable  
 refer to the SGS Tool Wizard® for complete technical information (www.kyocera-sgstoool.com)