

ISO-9001 Registered Quality System. ISO-21469 Compliant.

#### Sales, Service & Distribution Center

Newark, NJ 07105

Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605

Phone: 419-691-2491 Fax: 419-693-3806

**Sales and Tech Service Support** 

Phone: 1-800-733-4755

## **PRODUCT DATA**

# **LUBRIPLATE SYN LUBE SYNTHETIC FLUID SERIES**

No.'s 22, 32, 46, 68 & 100

## **DESCRIPTION**

LUBRIPLATE SYN LUBE ISO VG Fluids 22 through 100 are high performance, zinc-free synthetic fluids for industrial machine applications. These fluids are 100% synthetic based products formulated with a combination of PAO and ester technology.

## **ADVANTAGES**

LUBRIPLATE SYN LUBE Synthetic Fluids provide several advantages over mineral oil based products.

## **ENERGY SAVINGS**

SYN LUBE Synthetic Fluids exhibit high viscosity indexes, excellent lubricity, very low coefficients of friction and superior heat transfer characteristics, resulting in lower operating temperatures and lower power consumption

#### **EXTENDED DRAIN INTERVALS**

- Excellent thermal and oxidation stability characteristics increase the service life of the lubricant many times over that of petroleum oils
- Provide outstanding water demulsibility allowing for any water that may have entered the system to be rapidly separated from the SYN LUBE Synthetic Fluids. The water can then be easily drained and emulsion problems can be averted
- Generally, intervals of 8,000 hours of compressor fluid service can be achieved, depending on operating conditions. LUBRIPLATE Division encourages the use of our Free Oil Analysis Program to determine the extended drain interval

### FLUID/MATERIAL COMPATIBILITY

- ⇒ SYN LUBE Synthetic Fluids are compatible with mineral oil products avoiding time- consuming flushing procedures and allowing conversion to be simplistic. Always consult LUBRIPLATE prior to conversion if compatibility is an issue.
- ⇒ SYN LUBE Synthetic Fluids are recommended for use with high Nitrile Buna-N, Teflon, Viton, Fluorosilicone and Polysulfide elastomers. These fluids are **not** recommended for use with low Nitrile Buna-N, Neoprene or natural rubber

## Typical Test Data - See Back

## **APPLICATIONS**

LUBRIPLATE SYN LUBE Synthetic Fluids are available in (5) ISO Viscosity Grades (ISO VG 22, 32, 46, 68, and 100) and recommended for many types of rotary screw and rotary vane air compressors. These synthetic fluids are excellent for high temperature bearing and chain applications as well as situations striving for improved efficiency and extended drain intervals. They are also excellent products for centrifugal air compressors, all types of hydraulic systems and turbine oil applications.

| PACKAGING AVAILABLE     | SYN LUBE 22        | SYN LUBE 32 |
|-------------------------|--------------------|-------------|
| Carton, 4/1 Gallon Jugs | ***                | ***         |
| 5 Gallon Pail           | L0968-060          | L0970-060   |
| 55 Gallon Drum          | L0968-062          | L0970-062   |
| PACKAGING AVAILABLE     | <b>SYN LUBE 46</b> | SYN LUBE 68 |
| Carton, 4/1 Gallon Jugs | L0971-057          | L0972-057   |
| 5 Gallon Pail           | L0971-060          | L0972-060   |
| 55 Gallon Drum          | L0971-062          | L0972-062   |
| PACKAGING AVAILABLE     | SYN LUBE 100       |             |
| Carton, 4/1 Gallon Jugs | ***                |             |
| 5 Gallon Pail           | L0973-060          |             |
| 55 Gallon Drum          | L0973-062          |             |



# Typical tests for LUBRIPLATE SYN LUBE SYNTHETIC FLUID SERIES are as follows:

| PROPERTY                                       | TEST<br>METHOD | TYPICAL RESULTS*     |                      |                      |                      |                      |  |
|--|----------------|----------------------|----------------------|----------------------|----------------------|----------------------|--|
|  |                | SYN<br>LUBE 22       | SYN<br>LUBE 32       | SYN<br>LUBE 46       | SYN<br>LUBE 68       | SYN<br>LUBE 100      |  |
| Viscosity cSt @ 40°C                           | ASTM D-445     | 23                   | 32                   | 44                   | 66                   | 110                  |  |
| Viscosity cSt @ 100°C                          | ASTM D-445     | 5                    | 6                    | 8                    | 10                   | 15                   |  |
| Viscosity Index                                | ASTM D-2270    | 138                  | 136                  | 138                  | 138                  | 142                  |  |
| Pour Point                                     | ASTM D-97      | -70°F/-57°C          | -70°F/-57°C          | -65°F/-54°C          | -60°F/-51°C          | -55°F/-48°C          |  |
| Flash Point                                    | ASTM D-92      | 420°F/216°C          | 470°F/243°C          | 485°F/250°C          | 515°F/267°C          | 530°F/277°C          |  |
| Fire Point                                     | ASTM D-92      | 470°F/243°C          | 505°F/263°C          | 550°F/288°C          | 580°F/304°C          | 590°F/310°C          |  |
| API Gravity                                    | ASTM D-287     | 39.6                 | 37.0                 | 37.4                 | 37.8                 | 36.7                 |  |
| Color  | ASTM D-1500    | 1.0 max              |  |
| Density (Pounds/Gallon)                        |                | 6.89                 | 6.993                | 6.976                | 6.960                | 7.005                |  |
| ISO Viscosity Grade                            |                | 22                   | 32                   | 46                   | 68                   | 100                  |  |
| Auto ignition Temperature (734°F)              | ASTM E-659     | ND                   | >700°F               | >700°F               | >700°F               | >700°F               |  |
| 4-Ball Wear Test                               | ASTM D-4172    | 0.5mm                | 0.5mm                | 0.5mm                | 0.5mm                | 0.5mm                |  |
| Copper Corrosion                               | ASTM D-130     | 1a                   | 1a                   | 1a                   | 1a                   | 1a                   |  |
| Conradson Carbon Residue                       | ASTM D-189     | Nil                  | Nil                  | Nil                  | Nil                  | Nil                  |  |
| Emulsion Characteristics @ 82°C                | ASTM D-1401    | 40-40-0 (10)         | 40-40-0 (10)         | 40-40-0 (10)         | 40-40-0 (20)         | 40-40-0 (20)         |  |
| Rust Test Procedure B                          | ASTM D-665     | Pass No<br>Corrosion |  |
| Rotating Bomb Oxidation Test (Minutes)         | ASTM D-2272    | >2000                | >2000                | >2000                | >2000                | >2000                |  |
| Demulsibility Characteristics                  | ASTM D-2711    |                      |                      |                      |                      |                      |  |
| Procedure B; Run 1:<br>Percent of Water in Oil |                | 0.4%                 | 0.4%                 | 0.4%                 | 0.2%                 | 0.2%                 |  |
| Free Water Volume                              |                | 86.0 ml              | 86.0 ml              | 86.0 ml              | 84.0 ml              | 84.0 ml              |  |
| Emulsion Volume                                |                | 0.0 ml               |  |
| <b>Demulsibility Characteristics</b>           | ASTM D-2711    |                      |                      |                      |                      |                      |  |
| Procedure B; Run 2:<br>Percent of Water in Oil |                | 0.10%                | 0.10%                | 0.10%                | 0.3%                 | 0.3%                 |  |
| Free Water Volume                              |                | 87.8 ml              | 87.8 ml              | 87.8 ml              | 84.7 ml              | 84.7 ml              |  |
| Emulsion Volume                                |                | 0.0 ml               |  |
| Demulsibility Characteristics                  | ASTM D-2711    |                      |                      |                      |                      |                      |  |
| Procedure B; Average: Percent of Water in Oil  |                | 0.07%                | 0.07%                | 0.07%                | 0.3%                 | 0.3%                 |  |
| Free Water Volume                              |                | 86.9 ml              | 86.9 ml              | 86.9 ml              | 84.4 ml              | 84.4 ml              |  |
| Emulsion Volume                                |                | 0.0 ml               |  |

<sup>\*</sup>Values for typical results are for information only and can vary; these are not specifications.

Slight variations in product color may occur due to storage temperature and exposure to light. Product color has no impact on the lubricant's performance.